

Prajmer 2K PUR

Predpremaz za lepilo



Prajmer 2K PUR je predpremaz na bazi izocijanata i dodataka.

Tehničke karakteristike

Boja:	braon
Viskozitet, (RVT ISO 2555, A1/20/20 °C)	50-100 mPas
Sadržaj suve materije (DIN 53189)	56 ± 1%
Gustina	1010 kg/m ³
Potrošnja	0,3-0,35 l/m ²
Vreme sušenja na cementnim podlogama	24 časa
Rok upotrebe	8 meseci

Namena

Za impregnaciju betonskih podloga pre lepljenja parketa lepilima na bazi poliuretana (Elakol 2K PUR)

Uputstvo za upotrebu

Prajmer 2K PUR pre upotrebe potrebno je promešati. Preporučuje se nanošenje četkom u jednom sloju. Nakon upotrebe alat oprati sa etilacetatom.

Maksimalna vlažnost podloge koja se impregnira iznosi 4%.

Impregnaciju ne treba vršiti kod temperatura radnih prostorija nižih od 15 °C . Kako Prajmer otvrdnjava sa vazduhom ostatak nakon upotrebe potrebno je zatvoriti.

Pakovanje

Prajmer se isporučuje u ambalaži od 5 litara.

Skladištenje

U suvim prostorijama na temperaturi od +5 do +30 °C. Proizvod je vrlo osetljiv na vlagu. Kada se ambalaža otvori, sadržina mora što pre da se potroši.

Čuvati od smrzavanja.



Primer 2K PUR

Primer coating for adhesive



Primer 2K PUR is primer coating base on isocyanate and supplements.

Technical characteristics

Colour:	brown
Viscosity: (RVT ISO 2555, A1/20/20 °C)	50-100 m Pas
Dry matter: (DIN 53189)	56 ± 1%
Ashes:	45%
Density:	1010 kg/m ³
Consumption:	0.3-0.35 l/m ²
Drying time on cement surfaces	24 hours
Shelf life	8 months

Application

For impregnation of concrete surfaces before bonding parquet with polyurethane based adhesives (Elakol 2K PUR)

Introduction for use

Primer 2K PUR must be mixed before using. It is recommended application with brush in one layer. Wash the tools with ethyl acetate after using.

Maximum allowed humidity of the surface that is impregnated is 4%.

Impregnation shouldn't be done if the temperature in the working premises is lower than 15 °C . As Primer hardens in the open air, the rest of it must be well closed after usage.

Packing

Primer is delivered in packing of 5 liters.

Storage

Store in dry place, at temperatures from +5 to +30 °C. This product is sensitive to humid. Open product must be used as soon as possible.

Keep from freezing.

