

# ELANIT 161

Lepilo za industriju obuće i kožnu  
galanteriju



**Elanit 161** je jednokomponentno lepilo na bazi sintetičkog kaučuka rastvorenog u organskim rastvaračima. Otporno je na vodu i ulje.

## Tehničke karakteristike

Boja:	svetlo smeđa
Viskozitet: (FØ6)	180-200 s
Gustina:	0,90 g /cm <sup>3</sup>
Suva masa:	min 23 %
Rok upotrebe:	12 meseci
Potrošnja:	≈ 200g/m <sup>2</sup>

## Namena

Lepilo **Elanit 161** koristi se za lepljenje kože, neolit đona, poroznog krepa, tekstila i drugih materijala u industriji obuće i kožnoj galanteriji.

## Uputstvo za upotrebu

Pre upotrebe lepilo dobro promešati. Površine koje se lepe moraju biti suve i čiste. Pripremljene površine premazati (jednu i drugu stranu) tankim slojem lepila (kožu i porozne materijale dva puta). Sušenje traje 10-15 minuta, nakon čega se površine slepljuju i pritiskivanjem presuju. Pritisak presovanja kreće se od 300 do 400 kPa za vreme od 15 do 60 sekundi. Vezivanje traje 24 sata.

## Napomena

Uputstvo o načinu upotrebe prilagoditi lokalnim uslovima rada i materijalima koji se lepe.

## Pakovanje

Lepilo se isporučuje u ambalaži od 1, 4 i 20 litara.

## Skladištenje

U dobro zatvorenoj ambalaži, na suvom mestu na temperaturi od + 5° C do + 25° C (278K -298K)



# ELANIT 161

Adhesive for shoe and leather accessories industry



**Elanit 161** is a one component adhesive based on synthetic rubber dissolved in organic solvents. It is water and oil resistant.

## Technical characteristics

Colour:	light brown
Viscosity: (FØ6)	180-200 s
Density:	0.90 g /cm <sup>3</sup>
Dry matter:	min 23 %
Shelf life:	12 months
Consumption:	≈ 200g/m <sup>2</sup>

## Application

Adhesive **Elanit 161** is used for bonding leather, neolith sole, porous crepe, textile and other materials in shoe and leather accessories industry.

## Instruction for use:

Stir the adhesive well before using. Surfaces must be clean and dry. Apply the adhesive (on both sides of the surfaces) in thin layer (leather and porous materials twice). Allow the adhesive to dry for 10-15 minutes, and after that bond it and press. Pressure during pressing should be from 300 to 400 k Pa during time from 15 to 60 seconds. Bonding lasts for 24 hours.

## Note

Instruction for use should be adjusted according to local working conditions and bonding materials.

## Packaging

The adhesive is delivered in packaging from 1; 4 and 20 liters.

## Storage

Keep in well sealed packaging at temperatures from + 5° C to + 25° C (278K -298K)

