

ELANIT 171/s

Lepilo za posebne namene



Elanit 171/S je jednokomponentno lepilo na bazi poliuretana.

Fizičko-hemijske karakteristike

Boja:	transparentna
Viskozitet: FØ6	80-100 s
Gustina:	0,85 g/cm ³
Suva masa:	min 16 %
Potrošnja:	≈ 150 g/m ²

Namena

Lepilo **Elanit 171/S** se koristi za posebne namene.

Uputstvo za upotrebu

Pre upotrebe lepilo dobro promešati. Površine koje se lepe treba da budu čiste i suve. Lepilo se nanosi špricanjem na obe površine (promer dizne je 1,5 do 2,0 mm, pritisak 3-4 bara, udaljenost prskanja 25-30cm). Vreme sušenja je 5-10 minuta. Premazane površine aktivirati na temperaturi 70-80 °C. Nakon toga se vrši slepljivanje i presovanje materijala. Vreme vezivanja je 24 časa

Pakovanje

Lepilo se isporučuje u ambalaži od 1, 4 i 20 litara.

Napomena

Uputstvo o načinu upotrebe prilagoditi lokalnim uslovima rada i materijalima koji se lepe.

Skladištenje

U dobro zatvorenoj ambalaži, na suvom mestu na temperaturi od +5°C do +20 °C.



ELANIT 171/s

Special purposes adhesive



Elanit 171/S is one component adhesive based on polyurethane.

Physical- chemical characteristics

Colour:	transparent
Viscosity: FØ6	80-100 s
Density:	0.85 g/cm ³
Dry matter:	min 16 %
Consumption:	≈ 150 g/m ²

Application

Adhesive **Elanit 171/S** is used for special purposes.

Instruction for use:

Stir the adhesive well before using. Surfaces must be clean and dry. Apply the adhesive with spray on both surfaces in thin layer (diameter 1.5 to 2.0 mm, pressure 3-4 bars, spraying distance 25-30cm). Drying takes 5-10 minutes. Covered surfaces should be activated at temperature 70-80°C. After that proceed to bonding and pressing. Bonding time is 24 hours.

Packaging

The adhesive is delivered in packaging from 1; 4 and 20 liters.

Note

Instruction for use should be adjusted according to local working conditions and bonding materials.

Storage

Keep in well sealed packaging at temperatures from + 5° C to + 20° C



A. D. ELAN HEMIJSKA INDUSTRIJA, Ljubiše Miodragovića 11, 31300 Prijepolje, Srbija
tel: 00381 (033) 781 350; fax: 00381 (033) 780 005; e-mail: elanprodaja@ptt.rs; www.elan.rs